



1645 Haining Road  
 Vicksburg, Mississippi 39183-9036

## Product PV0004

### Typical Particle Size Distribution

(Determined by ASTM D5644)

Screen	% Retained
4 Mesh	0-5*
6 Mesh	41-71*
8 Mesh	24-47*
10 Mesh	0-12*
16 mesh	0-6*
20 mesh	0*

\*Typical ranges for most production runs

### Typical Chemical Properties

(Determined by ASTM D297 or TGA Analysis)

Chemical Parameter	Typical Range
Moisture	1.0% max
Metal	None
Acetone Extractables	8-20 %
Rubber Hydrocarbon (RHC)	46-58 %
Carbon Black	26-34 %
Ash	8 % max

888-638-8040

601-638-8040

601-638-6133 Fax

www.polyvulcusa.com

PCB1307  
 Effective date: 11/05/04



ISO9001:2000