



1645 Haining Road  
 Vicksburg, Mississippi 39183-9036

## Product PV0020

### Typical Particle Size Distribution

(Determined by ASTM D5644)

Screen	% Retained
14 Mesh	0
16 Mesh	0-2*
20 Mesh	0-15*
30 Mesh	12-38*
40 mesh	21-39*
60 mesh	19-35*

\*Typical ranges for most production runs

### Typical Chemical Properties

(Determined by ASTM D297 or TGA Analysis)

Chemical Parameter	Typical Range
Moisture	1.0% max
Metal	None
Acetone Extractables	8-20 %
Rubber Hydrocarbon (RHC)	46-58 %
Carbon Black	26-34 %
Ash	8 % max

888-638-8040

601-638-8040

601-638-6133 Fax

[www.polyvulcusa.com](http://www.polyvulcusa.com)

PCB1306  
 Effective date: 11/05/04



ISO9001:2000