



1645 Haining Road
Vicksburg, Mississippi 39183-9036

Product PV0040

Typical Particle Size Distribution

(Determined by ASTM D5644)

Screen	% Passing
20 Mesh	100
30 Mesh	95-100
40 Mesh	85-100
60 Mesh	30-60
80 mesh	15-40
100 Mesh	5-30

Typical Chemical Properties

(Determined by ASTM D297 or TGA Analysis)

Chemical Parameter	Typical Range
Moisture	0.75% max
Metal	None
Acetone Extractables	8-20 %
Rubber Hydrocarbon (RHC)	46-58 %
Carbon Black	26-34 %
Ash	8 % max

888-638-8040

601-638-8040

601-638-6133 Fax

www.polyvulcusa.com

PCB1301
Effective date: 10/17/03



ISO9001:2000