



1645 Haining Road
Vicksburg, Mississippi 39183-9036

Product PV0054

Typical Particle Size Distribution

(Determined by ASTM D5644)

Screen	% Retained
30Mesh	0
40 Mesh	0
60 Mesh	0-20
80 Mesh	15-45
100 mesh	
200 Mesh	

Typical Chemical Properties

(Determined by ASTM D297 or TGA Analysis)

Chemical Parameter	Typical Range
Moisture	0.75% max
Metal	None
Acetone Extractables	8-20 %
Rubber Hydrocarbon (RHC)	46-58 %
Carbon Black	26-34 %
Ash	8 % max

888-638-8040
601-638-8040
601-638-6133 Fax
www.polyvulcusa.com

PCB1309
Effective date: 10/17/03

