



1645 Haining Road
 Vicksburg, Mississippi 39183-9036

Product PV0080

Typical Particle Size Distribution

(Determined by ASTM D5644)

Screen	% Retained
30 Mesh	0
40 Mesh	0-T*
60 Mesh	0-3*
80 Mesh	5-18*
100 mesh	17-29*
200 Mesh	47-69*

*Typical ranges for most production runs

Typical Chemical Properties

(Determined by ASTM D297 or TGA Analysis)

Chemical Parameter	Typical Range
Moisture	0.75% max
Metal	None
Acetone Extractables	8-20 %
Rubber Hydrocarbon (RHC)	46-58 %
Carbon Black	26-34 %
Ash	8 % max

Products conform to Florida Department of Transportation requirements for Florida Type A

888-638-8040

601-638-8040

601-638-6133 Fax

www.polyvulcusa.com

PCB1303

Effective date: 11/05/04



ISO9001:2000