



1645 Haining Road
Vicksburg, Mississippi 39183-9036

Product PV0820

Typical Particle Size Distribution

(Determined by ASTM D5644)

Screen	% Retained
8 Mesh	0-1*
10 Mesh	8-25*
16 Mesh	47-60*
20 Mesh	15-29*
30 mesh	1-13*

*Typical ranges for most production runs

Typical Chemical Properties

(Determined by ASTM D297 or TGA Analysis)

Chemical Parameter	Typical Range
Moisture	1.0% max
Metal	None
Acetone Extractables	8-20 %
Rubber Hydrocarbon (RHC)	46-58 %
Carbon Black	26-34 %
Ash	8 % max

888-638-8040

601-638-8040

601-638-6133 Fax

www.polyvulcusa.com

PCB1308
Effective date: 11/05/04



ISO9001:2000