



1645 Haining Road
 Vicksburg, Mississippi 39183-9036

Product PV1030

Typical Particle Size Distribution

(Determined by ASTM D5644)

Screen	% Retained
10 Mesh	0-8
12 Mesh	7-21*
16 Mesh	28-44*
20 Mesh	18-30*
30 mesh	9-27*
40 Mesh	0-10*

*Typical ranges for most production runs

Typical Chemical Properties

(Determined by ASTM D297 or TGA Analysis)

Chemical Parameter	Typical Range
Moisture	1.0% max
Metal	None
Acetone Extractables	8-20 %
Rubber Hydrocarbon (RHC)	46-58 %
Carbon Black	26-34 %
Ash	8 % +/- 2%

888-638-8040

601-638-8040

601-638-6133 Fax

www.polyvulcusa.com

PCB1304
 Effective Date 11/4/04



ISO9001:2000