



1645 Haining Road
Vicksburg, Mississippi 39183-9036

Product PV4080

Typical Particle Size Distribution

(Determined by ASTM D5644)

Screen	% Retained
20 Mesh	0
30 Mesh	0-1
40 Mesh	0-15
60 Mesh	
80 mesh	
100 Mesh	0-15

Typical Chemical Properties

(Determined by ASTM D297 or TGA Analysis)

Chemical Parameter	Typical Range
Moisture	0.75% max
Metal	None
Acetone Extractables	8-20 %
Rubber Hydrocarbon (RHC)	46-58 %
Carbon Black	26-34 %
Ash	8 % max

888-638-8040
601-638-8040
601-638-6133 Fax
www.polyvulcusa.com

PCB1302
Effective date: 10/17/03

